

## TERPENE PHENOLIC RESIN

### Property & Usage

**SumRez™ Terpene Phenolic Resin** is made from gum rosin and phenol. It features a high softening point & light color, close distribution of molecular weight, superior tackifying ability & heat-resistance, extensive solvency & good phase with various kinds of elastomer or resin, and a longer period of the tackifying ability at early stage for solvent adhesive.

Usage in chloronorgutta rubber adhesive for PVC artificial leather, dismodule type of CR adhesive, hot-melt adhesive & adhesive tape, and sole adhesive of top grade shoes.

### Technical Data Sheet

TERPENE PHENOLIC RESIN	T8037	T803T
Appearance	irregular pieces	irregular pieces
Color (Gardner)	7 max.	10 max.
Softening point (R&B, deg C)	145 - 160	145 - 160
Acid value (mgKOH/g)	45 - 60	45 - 60

### Package & Note

<b>Package</b> 25kg net kraft polybag	<b>20'FCL load</b> 18mt (720bags)	<b>20'FCL palletized</b> 16mt (640bags)
<b>Chemical Formula</b> CH <sub>2</sub> O·W <sub>99</sub>	<b>CAS Number</b> 68240-08-4	<b>HS CODE</b> 39111000
<b>Standard</b> industry standard	<b>Storage</b> In cool place, avoid fire and high temperature.	

